



TEST REPORT

Applicant : Escorts Advanced Textiles Private Limited.
Contact Person : Mr. Shahid Mustafa
CC :
Address : 1st Floor, PHMA House, 33-A,
Block -D, New Muslim Town, Canal Road, Lahore,
Tel: +92 42 3780 9359
Fax: +92 42 3780 9360
E-mail:

Report No: 12807-25
Receiving Date: 25 April 2025
Issue Date: 30 April 2025

Manufacturer	: Escorts Advanced Textiles Private Limited.	Program	: /
Buyer	: Self Reference	Country of origin	: Pakistan
Agent	: /	Destination	: /
Label	: /	Size	: /
Content(Claimed)	: /	Season	:
Weight	: /	Department	: /
Previous Report No	: /	Protocol	: /
Design	: 220 grams/pair	End Use	: Heat Resistance Glove
Fabric	: Glove No 804		
Construction	: Terry Glove / Cotton		
Color	: Yellow		
Style	: /		
Style No	: /		
PO No	: /		
Vender Ref #	: Sample # 863		
Description	: Fabric Swatch		
Care instruction	: /		

For and on behalf of
TEXTILE TESTING INTERNATIONAL



Ali Ashraf
AVP Softlines



TEST REPORT

Report No: 12807-25

Test Summary:

Sr.		Pass	Fail	Remarks
1	Contact Heat	-	-	Level 3

Page 2 of 4

This test report is governed by the terms and conditions available overleaf or accessible at <http://ttilabs.net/terms&conditions.html>. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. The report is issued strictly based on the testing of the samples submitted by the customer. This test report may not be reproduced, except in full, without written approval of Textile Testing International.

**Report No:** 12807-25**Test Conducted****Requirements****1. Contact Heat**

EN 407:2020 § 4.5.3

Tested in accordance with EN ISO 12127-1:2015

Washing conditions:

EN ISO 6330: 2021

5 Washing cycles at 30 degree C

Program: 3N

Drying procedure: Flat dry

	<u>Temperature</u> <u>T_c (°C)</u>	<u>Threshold</u> <u>Time (Sec)</u>
Specimen 1	350	15.8
Specimen 2	350	16.1
Specimen 3	350	15.9
Minimum Time		15.8
Performance Level		3

Remarks: No signs of melting or dripping observed.

Test parameter	Table - Performance levels EN 407:2020 § 4.5.3			
	1	2	3	4
Contact temperature T _c (°C)	100°C	250°C	350°C	500°C
Threshold time t _i (sec)	≥ 15	≥ 15	≥ 15	≥ 15

Report No: 12807-25**Digital Image of Sample******** END OF REPORT ******

Page 4 of 4

This test report is governed by the terms and conditions available overleaf or accessible at <http://ttilabs.net/terms&conditions.html>. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. The report is issued strictly based on the testing of the samples submitted by the customer. This test report may not be reproduced, except in full, without written approval of Textile Testing International.